


Product Number: **0471**

Product Name: **Глясе**



**Iced coffee**

**Surface texture MFC boards**



**Mechanical and physical properties of MFC boards  
(TU 20.2- 323-44290-014:2004)**

Test designation	Unit	Values
Size	mm	2750 x 1830 2440 x 1830
Thickness	mm	10, 16, 18, 22, 25, 28
Density	kg/m <sup>2</sup>	640-740*
Bending strength	N/mm <sup>3</sup>	14-18*
Surface soundness, lower limit	N/mm <sup>3</sup>	0.8
Surface soundness, lower limit	N/mm <sup>3</sup>	0.6
Internal bound, lower limit	N/mm <sup>3</sup>	0.25 - 0.35*
Moisture content	%	5 - 12
Formaldehyde release: Class E1	mg/100g	< 8

**Tolerances on nominal dimensions**

Thickness	mm	± 0.3
Length and width	mm	± 5.0
Buckling, no more	mm/m	1.2
Resistance to pollution with substances of household purpose	visually	no changes
Specific resistance to high air visually	visually	no changes

\* depending on thickness

**Standard packaging MFC board**

Thickness, mm	Boards in pallet, number		Pallet weight, t(max)
	2750 x 1820	2440 x 1830	
16	40		2.29
18	36		2.29

